


RG Resin

RG from the Forward AM Ultracur3D® photopolymer resin line is a durable engineering material which can be used to print functional end-use parts. Its key feature is that it doesn't uptake any water and is suitable for a wide range of applications such as electrical cases, snappers and functional prototyping.



RG has passed the requirements associated with the following ISO 10993 biocompatibility tests.

| ISO Standard | Test Description | |
|--|--------------------------|--|
| ISO 10993-5: 2009 | In Vitro Cytotoxicity | |
| ISO 10993-11: 2017 | Pyrogen Test | |
| ISO 10993-11: 2017 | Acute Skin Toxicity Test | |
| ISO 10993-10: 2010 | Skin Sensitization Test | |
| ISO 10993-10: 2010; ISO 10993-2: 2006 | Skin Irritation Test | |

| | | Cured Parts | Standard |
|---------------------|--|----------------------|----------------|
| Tensile Properties | TENSILE STRENGTH | 60.4 MPa | ASTM D638 |
| | ELASTIC MODULUS | 1765 MPa | ASTM D638 |
| | ELONGATION AT BREAK | 11.7% | ASTM D638 |
| Flexural Properties | FLEXURAL STRENGTH | 77.7 MPa | ASTM D790 |
| | FLEXURAL MODULUS | 2.1 GPa | ASTM D790 |
| Thermal Properties | CTE @ 60C | 157 μm/m/°C | - |
| | HDT @ 0.45 MPa | 56.5 °C | ASTM D648 - 07 |
| General Properties | CONTACT ANGLE | 45-60° | ASTM D7334 |
| | WATER ABSORPTION (24h) | 0.77% | ASTM D570 |
| | DIELECTRIC CONSTANT (10 GHz) | 2.94 | - |
| | DF | 0.0197 | - |
| | HARDNESS | 77 Shore D | ASTM D785 |
| | VISCOSITY | 1100 cP | - |
| | STANDARD COLOR | Yellow trans / Black | - |
| | CELL CULTURE SURVIVAL RATE IN VITRO | 91.7% | - |
| | COMPATIBLE BMF SYSTEMS | S230, S240, S350 | - |

¹Final properties are dependent on print conditions, post-processing operations, and part

² Test samples were UV cured and heat cured.